

# Start saving energy now. Contact your local distributor.

**Unifrax Ltd.** 

T:+44 (0)1744 88 7600

www.unifrax.com

F:+44 (0)1744 88 9916

U-310 EN Rev: 1 Mar 10 Page 1 of 2

#### **DESCRIPTION**

Isofrax 1260°C Blankets are lightweight needled blankets manufactured from Isofrax alkaline earth silicate wool and provide effective solutions to a variety of thermal management problems. Isofrax 1260°C Blankets are completely inorganic and so retain their strength, flexibility and thermal properties in many working environments, without the generation of smoke or fumes. Available in a range of density and thickness combinations, Isofrax 1260°C Blankets can be used in a wide variety of high temperature applications.

# **GENERAL CHARACTERISTICS**

Isofrax 1260°C Blankets products have the following outstanding characteristics:

- High temperature stability
- Low thermal conductivity
- Resistance to thermal shock
- Good handling strength
- **Excellent flexibility**

# TYPICAL APPLICATIONS

- High temperature furnace and kiln linings
- **Boiler insulations**
- Pipe and duct insulation
- Heat shields

Any new and/or special use of these products, whether or not in an application listed in our literature, must be submitted to our technical department for their prior written approval.



# TYPICAL PRODUCT PARAMETERS

	Isof	rax 1260°C Blan	ket		
Typical Chemical Analysis (wt.%)					
SiO <sub>2</sub>		70.0 - 80.0			
MgO		>18.0 - 27.0			
Trace	<4.0				
Physical Properties					
Colour		White			
Melting Point (°C)		>1500			
Mean Fibre Diameter (microns)	4.5				
Density (kg/m³)	96	128	160		
Thermal Conductivity (W/mK)					
Mean Temp.					
400 °C	0.10	0.10	0.09		
600 °C	0.15	0.14	0.13		
800 °C	0.22	0.20	0.18		
1000 °C	0.31	0.27	0.25		
Tensile Strength (kPa)					
	25	40	40		

Isofrax products are suitable for a variety of high temperature applications. For specific advice on application and operational temperature limits please contact your nearest Unifrax Engineering office. Where appropriate Physical Properties data measured according to EN 1094-1.

# **AVAILABILITY**

Thickness (mm)	Density (kg/m³)			Roll Length (m)
	96	128	160	
13	✓	<b>√</b>		12.50
25	✓	<b>√</b>	<b>√</b>	7.32
38	<b>√</b>	<b>√</b>		5.00
50	✓	✓		3.66

Standard roll width is 610mm or 1220mm. Other thicknesses / sizes may be available on request subject to minimum order requirements. Versions with aluminium foil and other coverings are available subject to order.

# HANDLING INFORMATION

A Material Safety Data Sheet has been issued describing the health, safety and environmental properties of this product, identifying the potential hazards and giving advice on handling precautions and emergency procedures. This must be consulted and fully understood before handling, storage or use.

Supplied by:

Information contained in this publication is for illustrative purposes only and is not intended to create any contractual obligation. Further information and advice on specific details of the products described should be obtained in writing from a Unifrax Corporation company (Unifrax España, Unifrax France, Unifrax GmbH, Unifrax Limited, Unifrax s.r.o.). Unifrax maintains a continuous programme of product development and reserves the right to change product specifications without prior notice. Therefore, it maintains at all times the responsibility of the customer to ensure that Unifrax materials are suitable for the particular purpose intended. Similarly, insofar as materials not manufactured nor supplied by Unifrax are used in conjunction with or instead of Unifrax materials, the customer should ensure that all technical data and other information relating to such materials has been obtained from the manufacturer or supplier. Unifrax accepts no liability arising from the use of such materials. All sales made by a Unifrax Corporation company are subject to that company's Terms and Conditions of Sale, copies of which are available on request.